

# PS



## POLYSTYRENE

### Material description

PS is an amorphous thermoplastic with very low moisture absorption. PS in its pure form is very hard, brittle and for this reason unsuitable for applications subject to mechanical stress. Due to its low weather resistance, PS is unsuitable for outdoor use.

### Conformities

RoHS, REACH

Physical properties	Test method	Value	Unit
Density	DIN EN ISO 1183-1	1.04	g/cm3
Water absorbtion	DIN EN ISO 62	0.06	%
Sliding friction			
Abrasion resistance			

Mechanical properties	Test method	Value	Unit
Yield stress	DIN EN ISO 527	36	MPa
Elongation at break	DIN EN ISO 527	3	%
Tensile modulus of elasticity	DIN EN ISO 527	1000	MPa
Notched impact strength	DIN EN ISO 527	1850	kJ/m2
Shore Hardness D	ISO 868	76	

Thermal properties	Test method	Value	Unit
Thermal conductivity	DIN 52612-2	0.18	W/(m*K)
Coefficient of thermal expansion	DIN 53752	100	10 <sup>-6</sup> *K <sup>-1</sup>
Operating temperature short term		90	°C
Operating temperature long term		-60 bis 80	°C
Heat deflection temperature	DIN EN ISO 75 / A	86	°C
Flammability	UL 94, 3 mm	HB	

Electrical properties	Test method	Value	Unit
Volume resistivity	IEC 60093	10 <sup>16</sup>	Ω * cm
Surface resistivity	IEC 60093	10 <sup>14</sup>	Ω * cm
Dielectric strength	IEC 60243	65	kV/mm
Comparative tracking index (CTI)	IEC 60112	150	CTI

These technical data have been determined as average values by our suppliers from many individual measurements. In all measurements, the test specimens were tested in the dry state. We pass on the data with reservation. The table does not claim to be complete or correct. Material technology is subject to constant further development. No rights or guarantees can be derived from it. Own tests are necessary because the environmental and operating conditions (humidity, temperature, mechanical forces, radiation and chemicals, etc.) set limits in the application.